

**TYPICAL PROPERTIES OF TOYOLAC AX05 X03**

Typical Properties	Test Method	Test Conditions	Unit	Typical Value
Melt Flow Rate	ISO 1133	220 °C/10kg	g/10min	17
Charpy Impact, notched	ISO 179 / 1eA	23°C	kJ/m <sup>2</sup>	30
Deflection Temperature Under Load	ISO 75	120°C/hr, 1.8MPa	°C	80
Tensile Yield Stress	ISO 527	50 mm/min	MPa	47
Tensile Elongation	ISO 527	50 mm/min	%	>10
Tensile Modulus	ISO 527	1 mm/min	MPa	2100
Flexural Stress	ISO 178	2 mm/min	MPa	59
Density	ISO 1183		kg/m <sup>3</sup>	1040

Toray Plastics Malaysia Sdn. Bhd. (Head Office)  
 2628, MK1 SPT, Lorong Perusahaan 4 FIZ, Prai, 13600, Penang, Malaysia  
 Tel: 604-3988088 Fax: 604-3908975  
 Email : [sales.tpm@toray.com.my](mailto:sales.tpm@toray.com.my)  
[www.torayplastics.com](http://www.torayplastics.com)