

# TORAY PLASTICS (MALAYSIA) SDN BERHAD (46619-P)

2628, MK. 1, SPT., Lorong Perusahaan 4, Prai Free Industrial Zone, 13600 Prai,  
Penang, Malaysia.

Tel. No : 04-3988088

Fax. No: 04-3908975 (MD / Sales), 04-3974039 (Acct / Admin),  
04-3990563 (Purch), 04-3977357 (Material), 04-3997503 (Prod),  
04-3997502 (Eng), 04-3908977 (Tech)

## Abrasion Resistant ABS TOYOLAC™ 532 X02

| Property<br>代表物性                              | Test Method<br>试验法 | Test Conditions<br>试验条件 | Unit<br>单位        | TOYOLAC<br>532 X02 |
|---|--------------------|-------------------------|-------------------|--------------------|
| <b>Physical Properties 物理性能</b>               |                    |                         |                   |                    |
| Density<br>比重                                 | ISO 1183           | 23°C                    | kg/m <sup>3</sup> | 1050               |
| Melt Flow Rate<br>流动系数                        | ISO 1133           | 220°C, 10 kg            | g / 10min         | 22                 |
| <b>Mechanical Properties 机械性能</b>             |                    |                         |                   |                    |
| Charpy Impact,<br>Notched<br>缺口冲击强度           | ISO 179/1eA        | 23°C / 50% RH           | kJ/m <sup>2</sup> | 12                 |
| Tensile Strength<br>引张强度;降伏点                  | ISO 527            | 50 mm/min               | MPa               | 55                 |
| Tensile Elongation at Break<br>拉伸伸长率          |                    | 50 mm/min               | %                 | > 6                |
| Tensile Modulus<br>拉伸模数                       |                    | 1 mm/min                | MPa               | -                  |
| Flexural Strength<br>弯曲强度                     | ISO 178            | 2 mm/min                | MPa               | 78                 |
| Flexural Modulus<br>弯曲模数                      |                    |                         |                   | 2690               |
| <b>Thermal Properties 热性能</b>                 |                    |                         |                   |                    |
| Deflection Temperature<br>under load<br>热变形温度 | ISO 75             | 1.8 Mpa / 120°C/hr      | °C                | 83                 |
| <b>Flammability 燃烧性</b>                       |                    |                         |                   |                    |
| Flammability<br>燃烧性                           | UL 94              | -                       | -                 | HB                 |

Remark: These values are typical value for this product under specific test conditions and not intended for use as limiting specification.

「以上数据谨代表在特定条件下所得的测定值的代表例」