

Transparent Grade 透明型  
TOYOLAC™ 900 352 U

**FEATURE 特点**

Middle Impact Strength

中抗冲击

**APPLICATION 用途**

E&E Products, Household and Office  
Appliances, Toys

电子产品, 家电, 办公设备, 玩具, 一般应用

**TECHNICAL DATA SHEET 技术数据表**

| PROPERTY<br>性能                                         | TEST METHOD<br>测试方法      | TEST CONDITION<br>测试条件 | UNITS<br>单位 | TOYOLAC™<br>900 352 U |
|--------------------------------------------------------|--------------------------|------------------------|-------------|-----------------------|
| Physical Properties 物理性能                               |                          |                        |             |                       |
| Density<br>密度                                          | ISO 1183                 | 23 °C                  | kg/m³       | 1080                  |
| Melt Flow Rate<br>流动系数                                 | ISO 1133                 | 220 °C / 10 kg         | g/10 min    | 18                    |
| Mold Shrinkage<br>成型收缩率                                | ASTM D955                | 23 °C / 50% RH         | %           | 0.4 – 0.6             |
| Glass Content<br>玻纤含量                                  | –                        | –                      | –           | –                     |
| Mechanical Properties 机械性能                             |                          |                        |             |                       |
| Charpy Impact Strength,<br>Notched<br>Charpy 耐冲击强度, 缺口 | ISO 179/1eA              | 23 °C / 50% RH         | kJ/m²       | 12                    |
| Tensile Strength<br>拉伸强度-降伏点                           | ISO 527                  | 50 mm / min            | MPa         | 48                    |
| Tensile Elongation at<br>Break<br>拉伸伸长率-断裂点            | ISO 527                  | 50 mm / min            | %           | 12                    |
| Tensile Modulus<br>拉伸模数                                | –                        | –                      | –           | –                     |
| Flexural Strength<br>弯曲强度                              | ISO 178                  | 2 mm / min             | MPa         | 66                    |
| Flexural Modulus<br>弯曲模数                               | ISO 178                  | 2 mm / min             | MPa         | 1870                  |
| Thermal Properties 热性能                                 |                          |                        |             |                       |
| Deflection Temperature<br>Under Load<br>热变形温度          | ISO 75                   | 1.8 MPa / 120 °C/hr    | °C          | 76                    |
| Appearance 表面                                          |                          |                        |             |                       |
| Glossiness<br>光泽度                                      | –                        | –                      | –           | –                     |
| Light Transmittance<br>光线透光率                           | ASTM D1003               | 3 mmt                  | %           | 86                    |
| Haze<br>模糊系数                                           | ASTM D1003               | 3 mmt                  | %           | 2                     |
| Flammability 燃烧性                                       |                          |                        |             |                       |
| Flammability<br>燃烧性                                    | UL 94<br>File No. E41797 | –                      | –           | HB                    |

**Note:** The above values are typical data for the products under specific test conditions and not intended for use as limiting specifications.  
[ 以上数据谨代表在特定条件下所得的测定值的代表例 ]

TORAY PLASTICS (MALAYSIA) SDN BERHAD 东丽塑料大马有限公司  
197901002368 (46619-P)

No. 2628, MK 1, SPT, Lorong Perusahaan 4,  
Prai Free Industrial Zone,  
13600 Prai, Penang, Malaysia.  
Tel 电话: (60)4 - 398 8088  
Fax 传真: (60)4 - 390 8975, (60)4 - 397 7264  
URL 网址: [www.torayplastics.com.my](http://www.torayplastics.com.my)



Updated: 25-Mar-2024  
Version: 1.2