

Transparent Grade 透明型  
TOYOLAC™ A11C 333

**FEATURE 特点**

Good Colorability  
着色性

**APPLICATION 用途**

E&E Products, Household and Office Appliances, Personal Care, Toys  
电子产品, 家电, 办公室设备, 化妆品容器, 玩具, 一般应用

**TECHNICAL DATA SHEET 技术数据表**

PROPERTY 性能	TEST METHOD 测试方法	TEST CONDITION 测试条件	UNITS 单位	TOYOLAC™ A11C 333
<b>Physical Properties 物理性能</b>				
Density 密度	ISO 1183	23 °C	kg/m <sup>3</sup>	1070
Melt Flow Rate 流动系数	ISO 1133	220 °C / 10 kg	g/10 min	29
Mold Shrinkage 成型收缩率	ASTM D955	23 °C / 50% RH	%	0.3 – 0.4
Glass Content 玻纤含量	-	-	-	-
<b>Mechanical Properties 机械性能</b>				
Charpy Impact Strength, Notched Charpy 耐冲击强度, 缺口	ISO 179/1eA	23 °C / 50% RH	kJ/m <sup>2</sup>	1.5
Tensile Strength 拉伸强度-降伏点	ISO 527	50 mm / min	MPa	70
Tensile Elongation at Break 拉伸伸长率-断裂点	-	-	-	-
Tensile Modulus 拉伸模数	ISO 527	1mm / min	MPa	3800
Flexural Strength 弯曲强度	ISO 178	2mm / min	MPa	120
Flexural Modulus 弯曲模数	ISO 178	2mm / min	MPa	3700
<b>Thermal Properties 热性能</b>				
Deflection Temperature Under Load 热变形温度	ISO 75	1.8 MPa / 120 °C/hr	°C	86
<b>Appearance 表面</b>				
Glossiness 光泽度	-	-	-	-
Light Transmittance 光线透光率	ASTM D1003	3 mmt	%	90
Haze 模糊系数	ASTM D1003	3 mmt	%	2
<b>Flammability 燃烧性</b>				
Flammability 燃烧性	UL 94 File No. E41797	-	-	HB

**Note:** The above values are typical data for the products under specific test conditions and not intended for use as limiting specifications.  
[ 以上数据谨代表在特定条件下所得的测定值的代表例 ]

TORAY PLASTICS (MALAYSIA) SDN. BERHAD 东丽塑料大马有限公司  
197901002368 (46619-P)

No. 2628, MK 1, SPT, Lorong Perusahaan 4,  
Prai Free Industrial Zone,  
13600 Prai, Penang, Malaysia.  
Tel 电话: (60)4 - 398 8088  
Fax 传真: (60)4 - 390 8975, (60)4 - 397 7264  
URL 网址: www.torayplastics.com.my



Updated: 01-Apr-2022  
Version: 1.0